

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

(12) UK Patent Application (19) GB (11) 2 106 131 A

(21) Application No 8226855
(22) Date of filing 21 Sep 1982
(30) Priority data
(31) 305678
(32) 25 Sep 1981
(33) United States of America
(US)

(43) Application published
7 Apr 1983

(51) INT CL³
C07C 2/12

(52) Domestic classification
C5E 221 303 305 310
385 386 CF
U1S 1364 1420 1427
1511 C5E

(56) Documents cited
EPA 0030431
GB 1211973
GB 1155246

(58) Field of search
C5E

(71) Applicants
Chevron Research
Company
(USA—Delaware),
525 Market Street, San
Francisco, California,
United States of America

(72) Inventor
Stephen J Miller

(74) Agents
Haseltine Lake and Co.,
Hazlitt House, 28
Southampton Buildings,
Chancery Lane, London
WC2A 1AT

(54) Oligomerization of liquid olefins

(57) Oligomerization of liquid olefins is
effected using as catalyst an
intermediate pore size siliceous

crystalline molecular sieve which is
substantially free of hydrogen transfer
activity. The catalyst can be either a
zeolite such as ZSM—5 or ZSM—11
or a substantially alumina free silicate
such as silicalite.

GB 2 106 131 A

1 / 2




FIG. 1.




FIG._2.

SPECIFICATION

Oligomerization of liquid olefins

This invention relates to the preparation of heavy olefins by a catalytic oligomerization process.

Heavy olefins are chemicals which are highly useful and desirable compounds, especially when
5 they have only minor amounts of branching. These compounds can be used without further reaction as
components of functional fluids such as lubricants, as viscosity index improvers in lubricants, as
hydraulic fluids, as transmission fluids, and as insulating oils, e.g., in transformers to replace PCB
containing oils. Heavy olefins can also undergo chemical reactions to produce surfactants which in turn
10 can be used as additives to improve the operating characteristics of the compositions to which they are
added (e.g., lubricating oils), or can be used as primary surfactants in highly important activities such as
enhanced oil recovery. Among the most used surfactants prepared from heavy olefins are alkyl
sulfonates and alkyl aryl sulfonates.

It can be appreciated that there is a continuing search for more efficient methods for preparing
these highly desirable olefins.

15 The typical methods of preparing heavy olefins use 1-alkenes (alpha-olefins) as the reactants. In a
typical process, 1-octene, 1-decene, 1-tetradecene or mixtures thereof are oligomerized and heavy
olefin mixtures comprising trimers, tetramers and pentamers of the reactants are recovered. The
processes are typically catalytic and typically use multiphase systems.

Standard oligomerization processes use phosphoric acid containing catalysts to prepare gasoline
20 range materials. Three major modifications involving phosphoric acid catalysts include (1) quartz wetted
with liquid phosphoric acid, (2) phosphoric acid impregnated pellets (e.g., kieselguhr) used in reaction
chambers, and (3) phosphoric acid impregnated catalyst pellets packed in tubes surrounded by cooling
water. Additionally, copper pyrophosphate has been used as a catalyst.

More recent processes for producing heavy olefins for synthetic lubricants, as opposed to gasoline
25 range fuels, use boron trifluoride as the catalyst, together with promoters (e.g., BF_3 -decanol or BF_3 -
acetic acid complexes), or with cocatalysts. Reaction conditions typically include temperatures of less
than 100°C and pressures of less than 7 bar. The reactions are carried out in solutions which contain
the alkene reactants and the BF_3 -complex or the cocatalyst. Gaseous BF_3 is typically added by bubbling
through the solution. Cocatalysts include many organic compounds, such as esters, polyols, aliphatic
30 alcohols, aliphatic ethers, aliphatic carboxylic acids, ketones, aldehydes and acid anhydrides.

A number of patents have issued relating to the preparation of aromatics from short chain olefins
using highly active zeolites such as ZSM-5 (e.g., U.S. 3,756,942, Cattanch, September 4, 1973; U.S.
3,827,968, Givens et al., August 6, 1974; U.S. 3,960,978, Givens et al., June 1, 1976). Additionally,
several patents disclose the preparation of gasoline and fuel oil range materials from short chain olefins
35 such as propene and ethene (e.g., U.S. 4,227,992, Garwood et al., October 14, 1980; U.S. 4,211,640,
Garwood et al., July 8, 1980).

Even with the existence of phosphoric acid and zeolitic processes for making gasoline and of boron
trifluoride processes for making heavy olefins, it can be appreciated that there is a continuing search for
methods of heavy olefin preparation which use available materials, do not require solvent recovery steps
40 or use of liquid solutions, and yet which are efficient.

We have discovered that under certain reactions conditions, medium to long chain alkenes can be
polymerized over intermediate pore size crystalline molecular sieves to highly desirable heavier, long
chain alkenes. Surprisingly, intermediate pore size molecular sieves can catalyze these reactions even
45 though they would have been expected to crack or aromatize the feed alkenes. This discovery is
surprising because the art does not appear to have contemplated that longer chain materials could be
produced using medium to long chain alkenes as reactants over these molecular sieves. The reactants
have been thought to be too long to reach the catalytic active sites; and the active sites have been
thought to be too active to do any more than shorten the long reactant chain.

Further, not only are heavier, longer chain alkenes produced, they have sufficient branching to
50 have very low pour points, but not so much branching so as to have poor viscosity indexes. In addition,
the product heavy olefins have excellent characteristics and reactivity for further processing to make
surfactants useful in applications such as enhanced oil recovery and as lube oil additives. These
advantages are surprisingly achieved using pressures high enough to keep the reactants in the liquid
state while in the reaction zone and catalysts which have reduced hydrogen transfer activity.

55 Thus in accordance with the invention there is provided a process for preparing an alkene
oligomer, which comprises:

(a) contacting under oligomerization conditions a feed comprising at least one alkene which is a
liquid under said oligomerization conditions with a catalyst comprising an intermediate pore size
silicaceous crystalline molecular sieve (as hereinafter defined) substantially free of hydrogen transfer
60 activity; and

(b) recovering an effluent comprising an oligomerized alkene product derived from said liquid
alkene.

The feed may comprise or consist of a mixture of alkenes two or more of which are liquid under
the oligomerization conditions, in which case the effluent will contain alkene oligomers of the liquid

alkenes.

The feeds used in the process of the invention contain alkenes which are liquids under the conditions in the oligomerization reaction zone. Under standard operating procedures, it is normal both to know the chemical composition of feedstocks being introduced into a reaction zone and to set and control the temperature and pressure in the reaction zone. Once the chemical composition of a feedstock is known, the temperatures and hydrocarbon partial pressures which will maintain all or part of the feed as liquids can be determined using standard tables or routine calculations. Conversely, once the desired temperature and pressure to be used in the reaction zone are set, it becomes a matter of routine to determine what feeds and feed components would or would not be liquids in the reactor. These calculations involve using critical temperatures and pressures. Critical temperatures and pressures for pure organic compounds can be found in standard reference works such as *CRC Handbook of Chemistry and Physics*, *International Critical Tables*, *Handbook of Tables for Applied Engineering Science*, and Kudchaker, Alani, and Zwolinski, *Chemical Reviews*, 68, 659 (1968). The critical temperature for a pure compound is that temperature above which the compound cannot be liquefied regardless of pressure. The critical pressure is the vapor pressure of the pure compound at its critical temperature. These points for several pure alkenes are listed below:

		T_c °C (°F)	P_c -atm (bar)	
	ethene	9.21 (48.6)	49.66 (50.3)	
	propene	91.8 (197.2)	45.6 (46.2)	
20	1-butene	146.4 (295.5)	39.7 (40.2)	20
	1-pentene	191.59 (376.9)	40 (40.5)	
	iso-2-pentene	203 (397)	36 (36.5)	
	1-hexene	230.83 (447.49)	30.8 (31.2)	
	1-heptene	264.08 (507.34)	27.8 (28.2)	
25	1-octene	293.4 (560.1)	25.6 (25.9)	25
	1-decene	342 (648)	22.4 (22.7)	

It can be appreciated that at temperatures above about 205°C (401°F), pure C_5 and lower alkenes must be gaseous, while pure C_6 and higher alkenes can still be liquefied by applying pressure. Similarly, above about 275°C (527°F) pure C_6 and higher alkenes can be maintained in the liquid state, while pure C_7 and lower alkenes must be gaseous.

Typical feeds are mixtures of compounds. But even so, once the chemical composition of the feed is known, the critical temperature and pressure of the mixture can be determined from the ratios of the chemicals and the critical points of the pure compounds. See for example, the methods of Kay and Edmister in *Perry's Chemical Engineers Handbook*, 4th Edition, pages 3-214, 3-215 (McGraw Hill, 1963).

Of course, the only constraint on the alkenes present in the feed and which are to react in the oligomerization reaction zone is that these alkenes be liquids under the conditions in the reaction zone (the conditions include a temperature of less than about 350°C). The chemical composition of the alkenes can be varied to obtain any desired reaction mixture or product mix, so long as at least some of the alkene components of the feed are liquid.

The alkene chains can be branched. And, even though intermediate pore size molecular sieves are used, alkenes having quaternary carbons (two branches on the same carbon atom) can be used. But where quaternary carbons are present, it is highly preferred that the branches are methyl. It appears that even though the intermediate pore size molecular sieves do not admit quaternary carbon atoms into their pore structures, they have the capability of causing one of the quaternary substituents to migrate to a different position on the alkene chain, thereby forming two tertiary sites and an entity which can enter the intermediate sized pores.

The preferred alkenes are straight chain, or n-alkenes, and the preferred n-alkenes are 1-alkenes. The alkenes preferably have 8 or more carbon atoms, and more preferably have from about 9 to about 20 carbon atoms. Olefinic feeds which contain C_{15} — C_{20} olefins are particularly suitable for use, especially since these alkenes have a chain length which is awkward for many uses (too short for lubes, too long for detergents).

One of the surprising discoveries which the invention embodies is that under certain reaction conditions, longer chain alkenes can be polymerized over intermediate pore size molecular sieves

instead of being cracked to short chain compounds. Additionally, the oligomers produced from long n-1-alkenes are very highly desirable for use as lubricants. The oligomers have surprisingly little branching so they have very high viscosity indices, yet they have enough branching to have very low pour points.

- 5 The feed alkenes can be prepared from any source by standard methods. Often, suitable feeds are prepared from lower alkenes which themselves are polymerized into the appropriate range. Sources of such lower olefins can include FCC offgas, syngas (by use of CO reduction catalysts), low pressure, nonhydrogenative zeolite dewaxing, alkanols (using high silica zeolites), and dewaxing with crystalline silica polymorphs. Highly suitable n-1-alkene feeds, especially for preparing lubricating oil base stocks, can be obtained by thermal cracking of hydrocarbonaceous compositions which contain normal paraffins or by Ziegler polymerization of ethene.

- 10 By "intermediate pore size siliceous crystalline molecular sieve", as used herein, is meant two classes of silica containing crystalline materials. The first class includes materials which, in addition to silica, contain significant amounts of alumina. These crystalline materials are usually called "zeolites", i.e., crystalline aluminosilicates. The second class of materials are essentially alumina free silicates, e.g., CZM, and ferrosilicates, e.g., U.S. 4,238,318.

- 15 All of these materials have the ability of sorting molecules based on the size or the shape, or both of the molecules. The larger pore size materials will admit larger molecules than the smaller pore size materials. Intermediate pore size siliceous crystalline molecular sieves have the unique characteristics of being able to differentiate between large molecules and molecules containing quaternary carbon atoms on the one hand, and smaller molecules on the other. Thus, the intermediate pore size materials have surprising catalytic selectivities by reason of their effective pore apertures, as well as highly desirable and surprising catalytic activity and stability when compared to larger pore size crystalline molecular sieves.

- 20 By "intermediate pore size", as used herein, is meant an effective pore aperture in the range of about 5 to 6.5 Angstroms when the molecular sieve is in the H-form. Molecular sieves having pore apertures in this range tend to have unique molecular sieving characteristics. Unlike small pore zeolites such as erionite and chabazite, they will allow hydrocarbons having some branching into the molecular sieve void spaces. Unlike larger pore zeolites such as the faujasites and mordenites, they can differentiate between n-alkanes and slightly branched alkanes on the one hand and larger branched alkanes having, for example, quaternary carbon atoms.

- 25 The effective pore size of the molecular sieves can be measured using standard adsorption techniques and hydrocarbonaceous compounds of known minimum kinetic diameters. See Breck, *Zeolite Molecular Sieves*, 1974 (especially Chapter 8) and Anderson et al., *J. Catalysis* 58, 114 (1979). Intermediate pore size molecular sieves in the H-form will typically admit molecules having kinetic diameters of 5.0 to 6.5 Angstroms with little hindrance. Examples of such compounds (and their kinetic diameters in Angstroms) are: n-hexane (4.3), 3-methylpentane (5.5), benzene (5.85), and toluene (5.8). Compounds having kinetic diameters of about 6 to 6.5 Angstroms can be admitted into the pores, depending on the particular sieve, but do not penetrate as quickly and in some cases are effectively excluded. Compounds having kinetic diameters in the range of 6 to 6.5 Angstroms include: cyclohexane (6.0), 2,3-dimethylbutane (6.1), m-xylene (6.1), and 1,2,3,4-tetramethylbenzene (6.4). Generally, compounds having kinetic diameters of greater than about 6.5 Angstroms do not penetrate the pore apertures and thus are not absorbed into the interior of the molecular sieve lattice. Examples of such larger compounds include: o-xylene (6.8), hexamethylbenzene (7.1), 1,3,5-trimethylbenzene (7.5), and tributylamine (8.1).

- 45 The preferred effective pore size range is from about 5.3 to about 6.2 Angstroms. Among the materials falling within this range are the zeolite ZSM-5, the crystalline silica polymorphs, silicalite and RE 29,948 organosilicates, and the chromia silicate, CZM.

- 50 In performing adsorption measurements to determine pore size, standard techniques are used. It is convenient to consider a particular molecule as excluded if it does not reach at least 95% of its equilibrium adsorption value on the zeolite in less than about 10 minutes ($p/p_0 = 0.5$; 25°C).

- 55 Examples of intermediate pore size siliceous crystalline molecular sieves include zeolites such as members of the ZSM series, e.g., ZSM-5, ZSM-11, ZSM-12, ZSM-21, ZSM-23, ZSM-35, and ZSM-38. ZSM-5 is described in U.S. Nos. 3,702,886 and 3,770,614; ZSM-11 is described in U.S. 3,709,979; ZSM-12 is described in U.S. 3,832,449; ZSM-21 and ZSM-38 are described in U.S. 3,948,758; ZSM-23 is described in U.S. 4,076,842; and ZSM-35 is described in U.S. 4,016,245. The intermediate pore size materials can include "crystalline admixtures" which are thought to be the result of faults occurring within the crystal or crystallite area during the synthesis of the zeolites. The "crystalline admixtures" are themselves zeolites but have characteristics in common, in a uniform or nonuniform manner, to what the literature reports as distinct zeolites. Examples of crystalline admixtures of ZSM-5 and ZSM-11 are disclosed and claimed in U.S. 4,229,424. The crystalline admixtures are themselves intermediate pore size zeolites and are not to be confused with physical admixtures of zeolites in which distinct crystals or crystallites of different zeolites are physically present in the same catalyst composite or hydrothermal reaction mixture.

- 65 Other examples of intermediate pore size siliceous crystalline molecular sieves include

crystalline silica polymorphs which, as described before, are essentially alumina free.

"Essentially alumina free", as used herein, is meant the product silica polymorph (or essentially alumina-free siliceous crystalline molecular sieve) has a silica:alumina mole ratio of greater than 200:1, preferably greater than 500:1, and more preferably greater than 1000:1. The term "essentially alumina free" is used because it is difficult to prepare completely aluminum free reaction mixtures for synthesizing these materials. Especially when commercial silica sources are used, aluminum is almost always present to a greater or lesser degree. The hydrothermal reaction mixtures from which the essentially alumina free crystalline siliceous molecular sieves are prepared can also be referred to as being substantially aluminum free. By this usage is meant that no aluminum is intentionally added to the reaction mixture, e.g., as an alumina or aluminate reagent, and that to the extent aluminum is present, it occurs only as a contaminant in the reagents.

Intermediate pore size crystalline silicas include silicalite, disclosed in U.S. 4,061,724; the "RE 29,948 organosilicates" as disclosed in RE 29,948; and ZSM-48 as disclosed in European Patent Application No. 15132. Intermediate pore size silicas, ferrosilicates and galliosilicates are disclosed in U.S. 4,238,318. Intermediate pore size chromia silicates, CZM, are disclosed in U.K. Application Serial No. 2056961.

The most preferred molecular sieves are the zeolites ZSM-5, ZSM-11, and their crystalline admixtures, silicalite, RE 29,948 organosilicates, and CZM. Of course, these and other molecular sieves can be used in physical admixtures.

The siliceous crystalline molecular sieves must be substantially free of hydrogen transfer activity. High hydrogen transfer activity is typically present in a catalyst as a result of a high aluminum content (low silica:alumina mole ratio) in a molecular sieve component. If the silica:alumina ratio is low, the catalyst will tend to convert the olefinic products and reactants to paraffins and aromatics rather than to oligomerize them, thereby greatly reducing or eliminating the benefits of the present invention. (Hydrogen transfer activity is to be distinguished from hydrogenation activity, which would saturate the alkenes to produce the corresponding alkanes.) The hydrogen transfer activity of the molecular sieve can be substantially lessened by using essentially alumina free siliceous crystalline molecular sieves, and especially materials such as silicalite, the RE 29,948 organosilicates, and CZM.

Zeolitic siliceous crystalline molecular sieve catalysts can be made substantially more active and stable for oligomerization by including the Group IIB metals, zinc or cadmium. A primary characteristic of these substituents is that they are weak bases, and are not easily reduced. These metals can be incorporated into the catalysts using standard impregnation, ion exchange, etc., techniques. Other metals such as calcium and the rare earths may be included in the catalyst. If hydrogen is not added to the feed, Group VIII metals (such as nickel, cobalt, palladium, and platinum) as well as other metals (such as chromium, vanadium, titanium, manganese, and rhenium) may be included in the catalyst. Mixtures of these metals may also be present. Strongly basic metals such as the alkali metals are unsatisfactory as they poison substantially all of the polymerization sites on the zeolite. For this reason the alkali metal content of the zeolite is less than 1%, preferably less than 0.1%, and most preferably less than 0.01%. The most preferred substituents for use are zinc and cadmium, of these zinc is preferred. The amount of zinc or cadmium used is typically from about 0.01 to 10 weight percent.

The use of zinc or zinc compounds as the substituent on the zeolitic molecular sieves, and even on the essentially alumina free materials, gives surprising stability, yields, and activity in the liquid olefin oligomerization processes described herein.

The substantial absence of hydrogen transfer activity can be determined using standard laboratory procedures.

The polymerization processes of the present invention are surprisingly more efficient with small crystallite sieve particles than with larger crystalline particles. Preferably, the molecular sieve crystals or crystallites are less than about 10 microns, more preferably less than about 1 micron, and most preferably less than about 0.1 micron in the largest dimension. Methods for making molecular sieve crystals in different physical size ranges are known to the art.

The molecular sieves can be composited with inorganic matrix materials, or they can be used with an organic binder. It is preferred to use an inorganic matrix since the molecular sieves, because of their large internal pore volumes, tend to be fragile, and to be subject to physical collapse and attrition during normal loading and unloading of the reaction zones as well as during the oligomerization processes. Where an inorganic matrix is used, it is highly preferred that the matrix be substantially free of hydrocarbon conversion activity. It can be appreciated that if an inorganic matrix having hydrogen transfer activity is used, a significant portion of the oligomers which are produced by the molecular sieve may be converted to paraffins and aromatics and to a large degree the benefits of my invention will be lost.

The reaction conditions under which the oligomerization reactions take place include hydrocarbon partial pressures sufficient to maintain the desired alkene reactants in the liquid state in the reaction zone. Of course, the larger the alkene molecules, the lower the pressure required to maintain the liquid state at a given temperature. As described above, the operating pressure is intimately related to the chemical composition of the feed, but can be readily determined. Thus, the required hydrocarbon partial pressures can range from 26 bar at 290°C for a pure n-1-octene feed to about atmospheric pressure for

a n-1-C₁₅—C₂₀ alkene mixture. It is important to remember that while one process may introduce a liquid feed into a reaction zone and obtain a liquid product, the conditions in the reaction zone may be such that the reactants and products are gaseous while in the reaction zone. In the process of the invention, both reactant and product are liquids under the conditions in the reaction zone, thus leading to a high residence time of each molecule in the catalyst and thus to the very surprising oligomerization of molecules which the art has considered too large to function as reactants over intermediate pore size materials. 5

The reaction zone is typically operated below about 350°C. Above that temperature not only significant cracking of reactants and loss of oligomer product take place, but also significant hydrogen transfer reactions causing loss of olefinic oligomers to paraffins and aromatics take place. Liquid hourly space velocities can range from 0.05 to 20, preferably from 0.1 to about 4. 10

Once the effluent from the oligomerization reaction zone is recovered, a number of further processing steps can be performed.

If it is desired to use the long chain compounds which have been formed in lube oils as base stock, the alkene oligomers can be hydrogenated. 15

All of part of the effluent can be contacted with the molecular sieve catalyst in further reaction zones to further react unreacted alkenes and alkene oligomers with themselves and each other to form still longer chain materials. Of course, the longer the carbon chain, the more susceptible the compound is to being cracked. Therefore, where successive oligomerization zones are used, the conditions in each zone must not be so severe as to crack the oligomers. Preferably, the reaction conditions in each of the succeeding zones are less severe than in the oligomerization zone which immediately precedes it. Operating with oligomerization zones in series with decreasing severity can also make process control of the exothermic oligomerization reactions much easier. 20

One particularly desirable method of operation is to separate unreacted alkenes present in the effluent from the alkene oligomers present in the effluent and then to recycle the unreacted alkenes back into the feed. 25

The run life of the catalyst in the oligomerization reaction zone can be greatly and surprisingly increased by periodically stopping the flow of feed into the reaction zone and stripping the catalyst with a stripping gas (such as hydrogen, nitrogen, or water vapor). 30

In the accompanying drawings:
FIG. 1 illustrates data showing differences between the hydrogen transfer indices of several catalysts as well as the response of the hydrogen transfer indices to fouling; and 30

FIG. 2 shows the boiling point distribution of the product from codimerizing 1-decene and 1-tetradecene. 35

The invention is illustrated in the following Examples. 35

EXAMPLE 1

A series of experiments was performed to examine the hydrogen transfer activity of molecular sieves. A feed pulse of fixed volume (0.5 microliter) from a heated Valco valve was carried into a small, fixed catalyst bed located in a stainless steel reactor. The reaction was entirely gas phase and isothermal. The hydrocarbon feed pulse was carried to the catalyst bed by a known velocity nitrogen stream at a high linear rate. The nitrogen stream was passed through a 4A/5A molecular sieve purifier before contacting the feed. The catalyst bed contained -250 mesh catalyst fines which, depending on the catalyst, were diluted with the same size mesh alumina. The diluent alumina was added as needed to reduce the catalyst activity so all catalysts could be measured at roughly identical feed conversions. The catalyst was finally diluted (4:1) with 80—100 mesh, acid washed Alundum to improve catalyst dispersion and to help maintain a true isothermal bed temperature. Reactor pressure was controlled by an Annin valve. 40 45

The entire gas stream, containing the reacted feed pulse, was taken directly through heated lines to the injector splitter of a capillary gas chromatograph equipped with a flame ionization detector. 50

The reaction conditions include a catalyst temperature of 221°C (430°F), total pressure of 34.5 bar (500 psi) and a nitrogen carrier gas flow of 800 cc/min. at STP. The injection volume was 0.5 microliter. Hydrocarbon analysis was performed using a 50-meter OV-101 fused silica capillary column. The catalyst was continually exposed to the nitrogen carrier gas between injections. 50

The hydrogen transfer index calculated from the test results is the ratio of 3-methylpentenes to 3-methylpentane produced from a 1-hexene feed, with a linear hexene conversion from 30% to 70%. 55

The contact time was computed from the temperatures and pressure corrected linear velocity of the nitrogen carrier stream and the length and volume of the catalyst bed. The computed WHSV and catalyst/oil ratio were based solely on the active component content within the bed.

The catalysts tested are listed in Table 1.

TABLE 1

Catalyst	SiO ₂ /Al ₂ O ₃ Mole Ratio
(A) ZSM-5	78:1
(B) Silicalite	230:1
(C) Silicalite	2200:1
(D) Ultrastable Y	6:1
(E) Dealuminated Mordenite	63:1
(F) Amorphous SiO ₂ /Al ₂ O ₃	54/46 (wt. ratio)
(G) CZH-5	50:1

The results obtained are listed in Table 2. Experiments with Catalysts (A) and (B) were performed after impregnating the catalysts with 0.8 weight percent zinc.

TABLE 2

Catalyst	20% A 80% Al ₂ O ₃		20% A 80% Al ₂ O ₃		65% B	65% C	12% D 88% Al ₂ O ₃		18% E 82% Al ₂ O ₃	100% F	100% G
Inj. Number	3	3	3	3	3	2	3	3	1	2	1
Catalyst Wt (mg Sieve)	4.4	4.1	4.1	19	24	24	2.8	4.2	35	19.3	
Zn (0.8%) : Yes/No	No	Yes	Yes	Yes	No	No	No	No	No	No	No
Alundum Dilution	4:1	4:1	4:1	4:1	3:1	4:1	4:1	4:1	4:1	4:1	4:1
Contact Time (sec)	0.25	0.36	0.33	0.33	0.41	0.34	0.28	0.23	0.34	0.4	
WHSV (l/hr)	1100	806	200	120	1500	1220	100	157			
Cat/Oil	13	12	57	71	9	13	104	57			
Conversion From Linear Hexenes (%)	47	42	41	56	38	48	43	53			
K _{Hexenes} (l/sec)	2.54	1.51	1.60	2.00	1.71	2.84	1.65	1.88			
<i>Product Yield, Wt %</i>											
C ₄ Minus	13	12.6	14	13.3	3.5	17.1	0.3	12			
C ₅	11	10	8.4	8.5	4.2	12.9	3	8			
C ₆	57	58.8	62	53.6	63.2	55.7	76.4	73			
C ₇	4	4.2	4.1	5.5	4.7	4.4	3.5	2			
C ₈	7.5	5.6	5.4	7.9	5.9	5.2	4.1	3.7			
C ₉	4	3.6	2.5	4.3	4.3	2.4	2.4	1.3			
C ₁₀₊	1.9	2.8	2.3	4.9	10.7	1.1	10.1	0.3			
Hydrogen Transfer Index											
3M-Pentenes/3M-Pentane	66	70	105	500	0.30	1.0	5	6			

The graph of FIG. 1 illustrates the differences in hydrogen transfer index for several catalysts, as well as the response of the hydrogen transfer index to the number of hexene injections, i.e., to the fouling of the catalyst. The higher the hydrogen transfer index, the lower the hydrogen transfer activity of the catalyst. The hydrogen transfer index should be above 10, preferably above 25.

5 EXAMPLE 2

5

An experiment was performed to produce lubricant oil range materials from shorter chain length hydrocarbons. A 50/50 (wt.) mixture of 1-decene (b.p. 338°F) and 1-tetradecene (b.p. 419°F) was contacted with a Zn—ZSM-5 catalyst (1% Zn) at 232°C (450°F), hydrocarbon pressure of 27.6 bar (400 psig) and LHSV of 1. The product had the boiling characteristics shown by the distillation graph of FIG. 2. When the 329°C+ (625°F+) fraction of the product was hydrofinished, the pour point was less than -6.7°C (20°F) and the viscosity index was 105.

EXAMPLE 3

The alkene, 1-decene, was oligomerized over Zn—ZSM-5 (1% Zn) at 204°C (400°F), hydrocarbon pressure of 27.6 bar (400 psig) and LHSV of 1. The 1-decene was 46% converted with about 2% selectivity to C_9 , about 75% to 80% selectivity to C_{20} dimer, and about 11% selectivity to the C_{21+} fraction which primarily comprised C_{30} trimer.

EXAMPLE 4

An experiment was performed to examine dimerizing and trimerizing C_{10} alkenes, C_{15} — C_{20} alkenes, and their mixtures. The composition of the C_{10} alkenes feedstock used was:

20	1-alkenes	88%	20
	branched 1-alkenes	1%	
	branched internal olefins	4%	
	unbranched internal olefins	2%	
	diolefins	4%	
25	paraffins/naphthenes	0.7%/0.3%	25

The C_{15} — C_{20} alkene fraction had substantially the same composition but with some C_{21+} . The reactions were performed over a Zn (1 wt. %) ZSM-5/alumina (65/35 wt. %) catalyst at 27.6 bar (400 psig).

			Conversion, % Feed to:				
Hours On Stream	Temperature °C (°F)	LHSV	C ₂₂₊	C ₉₋			
5	Initial Feed — 3:1 (v/v) C ₁₅ —C ₂₀ :C ₁₀					5	
	25	232 (450)	0.75	24	3		
	91	232 (450)	0.50	32	1		
	139	232 (450)	0.50	17	<1		
	At 140 hours, the feed was changed to 100% C ₁₅ —C ₂₀						
10	184	204 (400)	0.50	26	2	10	
	231	182 (360)	0.50	6	<1		
				Conversion To:			
				C ₂₀₊	C ₃₀₊	C ₉₋	
	At 282 hours, the feed was changed to 100% C ₁₀						
15	304	246 (475)	0.50	27	9	4	15
	The catalyst was rejuvenated for 1 hour by stripping with hydrogen at 427°C (800°F). The unit was restarted with 100% C ₁₀ feed.						
	24	218 (425)	0.50	39	10	2	
	48	218 (425)	0.50	42	11	2	
20	These data show significant amounts of oligomerization with little cracking of products or reactants.						20

CLAIMS

1. A process for preparing an alkene oligomer, which comprises:
 - (a) contacting under oligomerization conditions a feed comprising at least one alkene which is a liquid under said oligomerization conditions with a catalyst comprising an intermediate pore size siliceous crystalline molecular sieve (as hereinbefore defined) substantially free of hydrogen transfer activity; and
 - (b) recovering an effluent comprising an oligomerized alkene product derived from said liquid alkene.
2. A process for oligomerizing alkenes, comprising:
 - (a) contacting under oligomerization conditions a feed comprising a mixture of alkenes wherein at least some of the alkenes in said alkene mixture are liquid under said oligomerization conditions with a catalyst comprising an intermediate pore size siliceous crystalline molecular sieve (as hereinbefore defined) substantially free of hydrogen transfer activity; and
 - (b) recovering an effluent comprising alkene oligomers of said liquid alkenes.
3. A process for oligomerizing alkenes, comprising:
 - (a) contacting under oligomerization conditions a feed consisting of an alkene mixture wherein at least some of the alkenes in said feed are liquid under said oligomerization conditions with a catalyst comprising an intermediate pore size siliceous crystalline molecular sieve (as hereinbefore defined) substantially free of hydrogen transfer activity; and
 - (b) recovering an effluent comprising alkene oligomers of said liquid alkenes.
4. A process according to Claim 1, wherein the feed comprises a mixture of alkenes two or more of which are liquid under said oligomerization conditions, and the effluent contains alkene oligomers of said liquid alkenes.
5. A process according to Claim 4, wherein substantially all of the alkenes in said alkene mixture are liquids under said oligomerization conditions.
6. A process according to Claim 4 or 5, wherein said oligomerization conditions include a temperature lower than the critical temperature of the alkene having the lowest critical temperature of the alkenes in said alkene mixture, and a pressure higher than the critical pressure of the alkene having the highest critical pressure of the alkenes in said alkene mixture.

7. A process according to any preceding claim, wherein said oligomerization conditions include a temperature of less than 350°C.
8. A process according to Claim 1, 2, or 3, wherein said alkenes comprise branched chain alkenes and wherein the branches of said branched chain alkenes are methyl branches.
- 5 9. A process according to any preceding claim, wherein the alkenes present in the feed are n-alkenes. 5
10. A process according to Claim 9, wherein said n-alkenes are 1-alkenes.
11. A process according to Claim 9 or 10, wherein said alkenes contain eight or more carbon atoms.
- 10 12. A process according to Claim 11, wherein said alkenes contain from 9 to 20 carbon atoms. 10
13. A process according to any preceding claim, wherein said catalyst incorporates zinc and/or cadmium in the form of the metal or a compound thereof.
14. A process according to any preceding claim, wherein said molecular sieve is the zeolite ZSM-5 or ZSM-11, or a crystalline admixture or physical admixture thereof.
- 15 15. A process according to any one of Claims 1 to 13, wherein said molecular sieve is substantially alumina free. 15
16. A process according to Claim 15, wherein said molecular sieve is silicalite, an RE 29,948 organosilicate, or CZM, or a mixture of two or more thereof.
17. A process according to any preceding claim, wherein said catalyst is periodically removed from contact with said feed, the catalyst is stripped with a stripping gas, and thereafter said contacting under oligomerization conditions is resumed. 20
18. A process according to any preceding claim, wherein the oligomerized alkene product is subjected to a hydrogenating step.
19. A process according to any one of Claims 1 to 17 and further comprising the steps of:
- 25 separating unreacted alkenes present in said effluent from alkene oligomers present in said effluent and recycling said unreacted alkenes back into the feed for said contacting step. 25
20. A process according to any one of Claims 1 to 17 and further comprising the step of contacting all or part of the effluent containing unreacted alkenes and alkene oligomers in at least one further oligomerization zone with a catalyst comprising an intermediate pore size siliceous crystalline molecular sieve (as hereinbefore defined) substantially free of hydrogen transfer activity under further oligomerization conditions which are not so severe as to crack oligomers present in the effluent from said further oligomerization zone. 30
21. A process according to Claim 20, wherein the further oligomerization conditions in said further zone are less severe than the reaction conditions of the oligomerization zone immediately preceding said further reaction zone. 35
22. A process in accordance with Claim 1 for preparing an alkene oligomer, substantially as described in any one of the foregoing Examples. 35